

Livaro Herringbone Dryback 150

technical data sheet

EN

Product specifications

Glue down LVT	EN ISO 10582	DoP LIV DB2026
Size		
	Box	26 / 2.925 m ² / 12.9 kg
	Pallet	84 boxes / 245.7 m ² / 1140 kg
Density	EN ISO 23996	± 1950 kg/m ³
Installation		Drop Lock
Different		24
Texture		Synchronous Wood Structure (EIR)
Surface		
Bevel		Regular bevel
Gloss level at 60°		2-4 %
Warranty conditions	Residential warranty	35 years
	Commercial warranty	20 years
Use class	EN ISO 10874	Class 23, Class 33, Class 42
		Heavy commercial use
		  

Empty fields indicate variations between the colors within the collection. Please refer to the table below for specific data per color.

Variables within the collection

Article Code	Finish	Texture	Bevel
LIV HB DB 150-647	Matt Gloss (2-4%)	Synchronous Wood Structure (EIR)	Regular bevel

Livaro Herringbone Dryback 150

technical data sheet

EN

Product properties				
property		test method	min. req.	result
Reaction to fire		EN 13501-1		Bfl-s1
Residual indentation		EN ISO 24343-1	≤ 0.1 mm	0.05 mm
Dimensional stability		EN ISO 23999	≤ 0.1 %	0.05 %
UV resistance		EN ISO 105-B02	≥ 6	> 6
Slip resistance		EN 13893 EN 16165	DS (≥ 0.3) / ≥ R9	DS (0.42) / R9
Scratch resistance		EN 16094	≤ MSR-A2 / ≤ MSR-B2	MSR-B1 MSR-A1
Stain resistance		EN 438-2		Group 1 and 2 : Grade 5 Group 3 : Grade 5
Effect of castor chair		EN 4918 (25000 cycles)	Slight change only	No visible damage
Furniture leg		EN 424	No visible change	No visible damage
Thermal resistance		EN 12664	< 0.15 m²K/W	0.011 m²K/W
Underfloor heating				OK (max +28°C)
Electrical properties (antistatic)		EN 1815	≤ 2.0	0.2 kV
Bacterial growth				Does not act as substrate
Impact sound reduction		EN ISO 10140		ΔL _{lin} 2 dB ΔL _w 3 dB

Livaro Herringbone Dryback 150

technical data sheet

EN

Environment				
property		test method	min. req.	result
Indoor air certifications/labels				Phthalate free, Greenguard, Floorscore, A+
REACH				Compliant
TVOC (28 days)		EN 16516		< 5 µg/m³
Pentachlorophenol content		CEN/TR 14823	< 5 ppm	< detectable limit
Recycled content				15 %
Formaldehyde emission				
CE-Marking - EN 14041		EN 717-1	≤ 0.124 mg/m³	E1
REACH Annex XVII Entry 77		EN 16516	< 0.080 mg/m³	< 0.005 mg/m³

Cleaning and maintenance instructions: www.parquetvinyl.com

